



TRIDAT

+ ACHIEVES FIRE CLASSIFICATION

+ PROTECTS COMBUSTIBLE ROOFING MEMBRANES



NO FIRE SPREAD
A2-s1,d0



50 m²

Thickness 0,41 mm
Weight 23 kg
1 m x 50 m





TRIDAT

GENERAL CHARACTERISTICS

Material	Glass fiber fabric
Thickness	0,41 mm
Mass per unit area	460 g/m ²

ESSENTIAL CHARACTERISTICS

Reaction to fire	A2-s1,d0	EN 13501-1
Temperature range	-36°C to 180°C	

ESSENTIAL CHARACTERISTICS

TENSILE STRENGTH		
Longitudinal direction (L)	1 300 N/50 mm	EN 12311-2
Transversal direction (T)	900 N/50 mm	EN 12311-2

PACKAGING CHARACTERISTICS

Width	1 m
Length	50 m
Total m ²	50 m ²
Weight	23 kg
Packaging	25 rolls/pallet (1 250 m ²)

**TECHNOPÔLE
SAINT-BRIEUC ARMOR**
5, rue Sophie Germain
22440 PLOUFRAGAN
FRANCE
T. +33 (0)2 96 78 24 22
export@winco-tech.com
www.winco-tech.com

